

Rustproof steel A2

General information

Designation	ISO 426/2 :	X8CrNiS 18 9 AISI 303
Material number	DIN 17'660 :	1.4305

Physical data

Density	:	7.9	g/cm ³
Elect. conductivity	:	1.37	MS/m

Mechanical data

Tensile strength	Rm :	500 – 700	N/mm ²
Yield strength	Rp0.2 :	195	N/mm ²
Ultimate strain	:	>35	%
Hardness	:	130-180	HB30

Composition

Carbon	C :	<0.12	%
Chrome	Cr :	17.0 – 19.0	%
Nickel	Ni :	8.0 – 10.0	%
Sulfur	S :	0.15 – 0.35	%
Manganese	Mn :	<2.0	%
Silicon	Si :	<1.0	%
Phosphor	P :	<0.06	%
Iron	Fe :	Residual	

Chemical resistance

Steel A2 is resistant under normal atmosphere for interior and outside applications, against diluted organic and oxidizing acids, caustic solutions, neutral and alkaline salt solutions as well as organic compounds. Steel A2 will be attacked by inorganic acids, halogens, chloride and chloridous solutions (e.g. sea water) or atmospheres (hole and stress corrosion).

AGRO AG

Hunzenschwil, October 22. 2024

This table is arranged to our best knowledge and is to advise you without obligation. All values are approximate values and are based on tests done by our suppliers. Modifications remain reserving.

AGRO AG CH-5502 Hunzenschwil

Tel. +41 62 889 47 47 · Fax +41 62 889 47 50 · info@agro.ch · www.agro.ch